



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter media

Polyester

Polyester

Appearance	White
Use	Pleatable filter media
Composition	100% Polyester Spunbonded
Area weight (g/m²)	270
Thickness (mm)	0.60
Air Permeability (m³/m²/h - 200 PA)	600
Surface electrical resistance (Ohm)	-
IFA/BIA certificate (DIN EN 60335-2-69:2008)	M
Max. working temperature (C°)	130
Volume of pores (%)	65
Application field	Gold, glass abrasives, welding fumes, talc, lime powder.